

# DESMODUR<sup>®</sup> 44V20L

**General Properties and Applications** Desmodur 44V20L is a liquid, dark brown mixture of diphenylmethane-4,4'-diisocyanate (MDI) with isomers and homologues of higher functionality. It is used in conjunction with polyols to produce rigid polyurethane foams.

**Sampling** Exposure to moisture must be prevented when taking product samples

Specification Property	Value	Unit of measurement	Method
NCO content	30.5 - 32.5	% by wt.	2011-0248603-94
Viscosity 25 °C*)	160 - 240	mPa·s	2011-0313703-95
Acidity	max. 200	ppm HCl	2011-0461102-96

\*) Lengthy storage can lead to an increase in the viscosity of Desmodur 44V20 L, although in our experience this has no adverse effect on the processing properties of the product.

Other Data* Property	Value	Unit of measurement	Method
Density 20 °C	approx. 1.23	g/cm <sup>3</sup>	DIN 51757
Phenylisocyanate content	max. 50	ppm	2011-0489801-95
Coefficient of thermal expansion	6.59 · 10 <sup>-4</sup>	K <sup>-1</sup>	
Specific heat (cp)	approx. 1.51	kJ/kgK	

\* These values provide general information and are not part of the product specification

**Packaging** Drums, IBCs, tank containers and tank wagons

**Storage** Recommended storage temperature: + 10 to + 30 °C (in exceptional cases up to 50°C)

Storage stability (ex works): 6 months if stored in moisture-tight drums

**Labeling** This product data sheet is only valid in combination with the corresponding current safety data sheet! Any updating of safety relevant information – in accordance with EU directives – will only be reflected in the Safety Data Sheet, copies of which will be revised and distributed. For further technical information relating to safety, the Safety Data Sheet should be consulted.

# DESMODUR<sup>®</sup> 44V20L

## Directions for Processing

Desmodur 44V20 L may undergo partial crystallization at temperatures below 0 °C. The product can, however, be brought back into the liquid state by heating the entire contents of the drum for a short time to a maximum of 70 °C, although this may lead to an increase in the solids content.

Drums including empty ones should always be kept tightly sealed. The product should never be allowed to come into contact with water, which reacts with Desmodur 44V20 L to form polyureas and carbon dioxide. Contact with water in any form (damp drums, solvents containing water, moist air) must be prevented not only during storage, but also when removing material from drums and during processing. Failure to do so may lead to a dangerous build up of pressure in tanks and drums due to the generation of carbon dioxide. In addition, polyureas forming in Desmodur 44V20 L can cause solids to separate out, leading to blockages in the filters, pumps and pipelines of the processing equipment and resulting in production problems.

The following information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Insofar as Bayer MaterialScience AG is not responsible for damages caused intentionally or through gross negligence, we shall not be liable for consequential damages or purely financial losses. The above limitation shall not apply to damage resulting from death, injury or damage to health. None of the above shall affect any statutory liability rights. Our advice does not release you from the obligation to check its validity and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Editor: Business Unit Polyurethanes  
Bayer MaterialScience AG,  
D-51368 Leverkusen, Germany  
[www.bayermaterialscience.com](http://www.bayermaterialscience.com)

**Contact :**  
Brassat, Dr. Lutz  
Tel. +49 214 / 30-46805

page 2 of 2

Edition 2007-05-24

Replaces edition dated 2006-06-21

**DESMODUR<sup>®</sup>**

Product Datasheet