

ELVACITE 2013 ACRYLIC RESIN

Typical Properties:-

Glass Transition Temperature (d.Cel.)	76
Molecular Weight	34,000
Form	Spherical beads
Particle Size (D50)	160-200 microns
Specific Gravity	1.15
Inherent Viscosity	0.156 - 0.174
Acid Number	5
Moisture (% max.)	0.35
Tukon Hardness, Knoop NO.	13
Tensile Strength, psi	1,600
Elongation at break (23 deg.C, 50% RH)	0.50%
Packaging	136 kg (300 lb. net)
	non- returnable fiber drums